

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**


Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**



Eur päis hes Pat ntamt  
European Pat nt Offic  
Office européen d s br v ts



(11) **EP 0 408 311 B1**

(12)

# EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention  
of the grant of the patent:  
**02.10.1996 Bulletin 1996/40**

(51) Int Cl.<sup>6</sup>: **C08F 230/08, A61K 7/06**

(21) Application number: **90307528.1**

(22) Date of filing: **10.07.1990**

(54) **Polymer for hair-care products**

Polymer für Haarpflegemittel

Polymères pour des produits de traitement des cheveux

(84) Designated Contracting States:  
**DE FR GB IT**

(30) Priority: **12.07.1989 JP 179811/89**

(43) Date of publication of application:  
**16.01.1991 Bulletin 1991/03**

(73) Proprietor: **MITSUBISHI CHEMICAL  
CORPORATION**  
Chiyoda-ku, Tokyo-to (JP)

(72) Inventors:  
• **Hayama, Kazuhide, C/o Mitsubishi Petr. Co. Ltd.**  
Yokkaichi-Shi, Mie-Ken (JP)

• **Narazaki, Kanji, C/o Mitsubishi Petr. Co. Ltd.**  
Yokkaichi-Shi, Mie-Ken (JP)  
• **Kawaguchi, Sigeoki,**  
C/o Mitsubishi Petr. Co. Ltd.  
Yokkaichi-Shi, Mie-Ken (JP)

(74) Representative: **Kyle, Diana et al**  
Elkington and Fife  
Prospect House  
8 Pembroke Road  
Sevenoaks, Kent TN13 1XR (GB)

(56) References cited:  
**EP-A- 0 294 515 WO-A-88/05060**  
**FR-A- 2 296 402 FR-A- 2 465 236**  
**US-A- 4 693 935**

Note: Within nine months from the publication of the m ntion of the grant of the European patent, any person may giv notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall b filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

**EP 0 408 311 B1**

**Description**

The present invention relates to novel polymers suitable for use in hair-care products. More particularly, the present invention relates to a polymer comprising as an essential constituent units of a hydrophilic unsaturated monomer which affords hair an excellent brilliance and gloss and a smooth feeling and has an excellent washability, and into which a polysiloxane group has been introduced.

The polymers in accordance with the present invention can be used for providing hair with settability, softness, gloss, smooth feeling, smooth combing, recovery from damages, manageability and the like.

In hair-care products such as a shampoo, a rinse, a hair treatment product, a hair setting product or a cold permanent wave solution have heretofore been used oily components such as silicone compounds, ester compounds, hydrocarbon compounds or the like in an emulsified, solubilized or dissolved state, for the purpose of providing hair with brilliance, gloss and smoothness. The silicone type compounds among them have these years been used extensively because of their excellent properties.

Specific examples of application of silicone compounds include (i) hair-care products into which silicone oils such as polydimethylsiloxane, polymethylphenylsiloxane or the like and their emulsion have been incorporated; (ii) aerosol foam type hair setting products such that an etherified silicone such as a polydimethylsiloxane-polyoxyalkylene block copolymer or the like has been incorporated into a hair-fixative polymer such as a cationic polymer or an amphoteric polymer to form, together with a propellant, the aerosol products (Japanese Patent Laid-Open Publication No. 135319/88); (iii) shampoos and rinses into which an aminated organopolysiloxane emulsion has been incorporated (Japanese Patent Laid-Open Publication No. 307811/63); (iv) hair conditioning product and hair-setting products such that an aminated organopolysiloxane emulsion has been incorporated into a cationic polymer compound and an amphoteric polymer compound, respectively, to form the hair conditioning product and hair-setting products (Japanese Patent Laid-Open Publication No. 275515/88); and (v) hair-care products in which polydimethylsiloxane or polymethylphenylsiloxane having a high molecular weight is used (Japanese Patent Laid-Open Publication No. 243019/88).

However, the silicone oils or the etherified silicones when used may cause problems such as giving sticky feeling to hair or undergoing reverse transition of silicone from hair to hand or clothing if they are formulated in a large amount or if the product is used repeatedly for a long time. Emulsions of silicones may have problems in dispersion stability. Silicones having a high molecular weight may have problems in the compatibility with hair care resins or additives, so that they have restrictions in formulation whereby their applicability in a variety of hair-care products is restricted.

The silicone compounds having no such hydrophilic groups as a polyether group are difficult to be removed by usual hair washing, and thus when consumers use the products into which the less hydrophilic silicone compounds have been formulated for a long period repeatedly, hair tends to be hydrophobic and causes problems in hair dyeing or permanent waving.

The object of the present invention is to solve the aforementioned problems and to provide a polymer for hair-care products which provides hair with an excellent gloss and brilliance and a smooth feeling without stickiness and will not be accumulated in the hair and cause no problems for being formulated into cosmetics.

The invention provides use in a hair-care product of a copolymer comprising (a) a unit of a hydrophilic ethylenically unsaturated monomer in a quantity of 15 to 99.9% by weight; (b) a unit of an ethylenically unsaturated monomer having a polysiloxane group in a quantity of 0.1 to 85% by weight; and (c) a unit of a hydrophobic ethylenically unsaturated monomer in a quantity of 0 to 84.9% by weight. In a hair care product comprising said copolymer, the copolymer is dissolved in water and/or alcohol in a concentration of 0.5 to 10 % by weight.

In the present invention, an ethylenically unsaturated monomer having a polysiloxane group (b) is copolymerized with a hydrophilic ethylenically unsaturated monomer (a) and, if necessary, with a hydrophobic ethylenically unsaturated monomer (c), so that the defects in conventional silicone compounds such as generation of the sticky feeling of hair or the reverse transition of silicone encountered when the silicone compounds are formulated in a large quantity or on the use for a long period repeatedly can be solved thanks primarily to the use of the compound (b), and the silicone can be easily removed by washing hair thanks primarily to the component (a). Further, a hydrophilic ethylenically unsaturated monomer component (a) and a hydrophobic ethylenically unsaturated monomer component (c) are appropriately chosen in terms of their types and relative proportions, so that the polymer can now be incorporated into hair care products without restriction.

**DESCRIPTION OF THE PREFERRED EMBODIMENT OF THE INVENTION****[I] Polymer****Unsaturated Monomer**

The polymer suitable for use in the present invention is obtained by copolymerizing two essential monomers,

namely (a) a hydrophilic unsaturated monomer and (b) an unsaturated monomer having a polysiloxan group, and an optional monomer, namely (c) hydrophobic unsaturated monomer. Each of these monomers of the categories (a), (b) and (c) can be used in admixture within respective categories.

5 Hydrophilic unsaturated monomers (a):

Preferably, the hydrophilic unsaturated monomers as the component (a) are hydrophilic unsaturated monomers of a cationic, anionic, nonionic or amphoteric nature and polymerizable through radical polymerization mechanism. It is preferable that they have a solubility in water in a range of 10 g/100 g of water or more (25°C).

10 Examples of the cationic unsaturated monomers include

- (i) monomers derived from acrylic acid or methacrylic acid, which is referred to hereinafter collectively as (meth) acrylic acid, and a quaternarized epihalohydrin product of a trialkylamine having 1 to 4 carbon atoms in the alkyl such as (meth)acryloyloxyhydroxypropyltrimethylammonium chloride and (meth)acryloyloxyhydroxypropyltriethylammonium bromide;
- (ii) amine derivatives of (meth)acrylic acid or amine derivatives of (meth)acrylamide derived from (meth)acrylic acid or (meth)acrylamide and a dialkylalkanolamine having C<sub>1</sub> to C<sub>4</sub> alkyl groups such as dimethylaminoethyl (meth)acrylate, diethylaminoethyl (meth)acrylate, dimethylaminopropyl (meth)acrylate, or dimethylaminopropyl (meth)acrylamide; and
- (iii) derivatives of the products of the group (ii) above by (1) neutralization with an acid such as hydrochloric acid, or lactic acid, (2) denaturation with a halogenated alkyl such as methyl chloride, ethyl chloride, methyl bromide, or ethyl iodide, (3) denaturation with a halogenated fatty acid ester such as ethyl monochloroacetate, or methyl monochloropropionate, and (4) denaturation with a dialkyl sulfate such as dimethyl sulfate, or diethyl sulfate.

25 Furthermore, the cationic unsaturated monomers include amine derivatives of allyl compounds such as diallyldimethylammonium chloride and the like.

These cationic unsaturated monomers can be copolymerized in the form as such, or as an alternative they can be copolymerized in the form of their precursors, which are then cationized by a so-called cationizing agent. More particularly, dimethylaminoethyl (meth)acrylate is copolymerized, and the copolymer obtained will then be cationized by a quaternizing agent such as hydrochloric acid, ethyl monochloroacetate, dimethyl sulfate to form a desired copolymer of the cationic unsaturated monomer.

Examples of the anionic unsaturated monomers include:

- (i) unsaturated carboxylic acid monomers such as (meth)acrylic acid, maleic acid, maleic anhydride, itaconic acid, fumaric acid, and crotonic acid;
- (ii) half esters of an unsaturated polybasic acid anhydride such as succinic anhydride, phthalic anhydride with a hydroxyl group-containing (meth)acrylates such as hydroxyethyl (meth)acrylate, hydroxypropyl (meth)acrylate,
- (iii) monomers having a sulfonic acid group such as styrenesulfonic acid, sulfoethyl (meth)acrylate, and
- (iv) monomers having a phosphoric acid group such as acid phosphoxyethyl (meth)acrylate, 3-chloro-2-acid phosphoxypropyl (meth)acrylate.

These anionic unsaturated monomers can be used in the form of an acid or after partial or complete neutralization, or they can be copolymerized in the form of acid and then neutralized partially or completely. Examples of the bases used for neutralization include alkali metal hydroxides such as lithium hydroxide, potassium hydroxide, sodium hydroxide, aqueous ammonia, amine compounds such as mono-, di- or triethanolamine, triethylamine, morpholine, aminomethylpropanol, aminoethylpropanediol.

Examples of the nonionic unsaturated monomers include monomers derived from (meth)acrylic acid or (meth)acrylamide and an alkylene oxide having 2 to 4 carbon atoms such as hydroxyethyl (meth)acrylate, polyethyleneglycol mono(meth)acrylate, methoxypolyethyleneglycol mono(meth)acrylate, methoxypoly(ethylene glycol/propylene glycol) mono(meth)acrylate, polyethylene glycol di(meth)acrylate, N-polyalkylenoxy(meth)acrylamide; acrylamide, N-vinylpyrrolidone.


Examples of the amphoteric monomers include zwitter ionized derivatives of the aforementioned amine derivatives of (meth)acrylic acids or the amine derivatives of (meth)acrylamide such as dimethylaminoethyl (meth)acrylate, dimethylaminopropyl(meth)acrylamide by a halogenated fatty acid salt such as potassium monochloroacetate, sodium monobromopropionate, aminomethylpropanol salt of monochloroacetic acid, triethanolamine salt of monochloroacetic acid; and modified products with propanesultone of the aforementioned amine derivatives of (meth)acrylic acid or (meth)acrylamide.

These amphoteric unsaturated monomers, like the aforementioned cationic unsaturated monomers, can be copoly-

lymerized in the form as such or as an alternative they can also be copolymerized in the form of their precursors, which are then converted into amphoteric state. It is also possible to remove the salt produced as a by-product of amphotericization by filtration or ion-exchange, if necessary, before copolymerization step or after the copolymerization-amphotericization step. These technologies are described in detail in Japanese Patent Laid-Open Publication No. 92809/81.


The hydrophilic unsaturated monomer is used in an amount of 15 to 99.9% by weight per weight of total monomers. If the amount is less than 15% by weight, the copolymer thus obtained has problems that it is hardly soluble in water and/or an ethanolic solvent or it is difficult to be removed upon hair washing. The amount of the monomer can be selected at will according to the uses with the upper limit of 99.9% by weight. In other words, the hydrophilic unsaturated monomer is preferably used in an amount of 15 to 59.5% by weight when the polymer is used as a hair-setting polymer and 30 to 99.5% by weight when the polymer is used as a hair-conditioning polymer. Polysiloxane group containing unsaturated monomer (b):

The polysiloxane group-containing unsaturated monomer as the component (b) is a monomer which has at least one unsaturated group having radical polymerizability and a polysiloxane group



wherein  $a = 1$  to 150.

Specifically, compounds represented by the following formula (I) are mentioned:



wherein D,  $\text{R}_1$ ,  $\text{R}_2$ , m and n have the following meanings, respectively:

D = an unsaturated group having radical polymerizability such as a vinyl group, a vinylalkylene group, a vinylhydroxyalkylene group, an acryloyloxyalkylene group, a methacryloyloxyalkylene groups, an acryloyloxyhydroxyalkylene group and a methacryloyloxyhydroxyalkylene group;

$\text{R}_1$  = a hydrogen atom, a phenyl group, an alkyl group having 1 to 10 carbon atoms, a polyoxyalkylene group, a polyoxyalkylene group of which end has been substituted by an ether or ester group, a polyalkylenepolyamine group, a fatty acid group or a polysiloxane group, respectively;




$\text{R}_2$  = a hydrogen atom, a phenyl group, an alkyl group having 1 to 10 carbon atoms, a polyoxyalkylene group, a polyoxyalkylene group of which end has been substituted by an ether or ester group, a polyalkylenepolyamine group, a fatty acid group or a polysiloxane group, or an unsaturated group having radical polymerizability such as a vinyl group, a vinylalkylene group, a vinylhydroxyalkylene group, an acryloyloxyalkylene group or a methacryloyloxyalkylene group;

m = an integer from 4 to 150; and

n = an integer from 0 to 150, wherein the sum of m and n is within 150.

In the above-described formula (I), the sum of m and n is preferably in the range of 4 to 150. If the sum is less than 4, the polymer obtained by the copolymerization cannot exhibit the advantages inherent in the silicone compound. If the sum exceeds 150, the copolymerizability with the unsaturated monomers of the components (a) and (b) is undesirably lowered.

Embodiments of the unsaturated monomer having a polysiloxane group include the unsaturated monomers illustrated by the following formulae (II) - (IV):



wherein  $\text{R}_3$  -  $\text{R}_5$ ,  $p$  and  $q$  have the following meanings independently of each other between the formulae:

$\text{R}_3$  = a hydrogen atom or a methyl group;

$\text{R}_4$  = an alkylene group having 1 to 4 carbon atoms;

$\text{R}_5$  = an alkyl group having 1 to 10 carbon atoms or a phenyl group;

$p$  = an integer of 1 or more; and

$q$  = an integer of 1 or more, wherein the sum of  $p$  and  $q$  are within 150.


The unsaturated monomers illustrated by the general formula (II) can be obtained as commercially available products (manufactured by Chisso Corporation) such as FM0711 (trade name;  $p = 10$ ,  $\text{R}_3$  = a methyl group,  $\text{R}_4$  = a propylene group, and  $\text{R}_5$  = a methyl group in the aforementioned formula (II); referred to as polysiloxane FM0711 in the preparation example below), FM0721 ( $p = 60$ ,  $\text{R}_3$  = a methyl group,  $\text{R}_4$  = a propylene group, and  $\text{R}_5$  = a methyl group in the aforementioned formula (II); referred to as polysiloxane FM0721 in the preparation example below) and FM0725 ( $p = 130$ ,  $\text{R}_3$  = a methyl group,  $\text{R}_4$  = a propylene group, and  $\text{R}_5$  = a methyl group in the aforementioned formula (II); referred to as polysiloxane FM0725 in the preparation example below).

The monomers illustrated by the general formula (III) can be easily obtained by the reaction of a polysiloxane having both ends of silanol and a (meth)acryloyloxyalkylene (having 1 to 4 carbon atoms) di(alkyl (having 1 to 4 carbon atoms) or phenyl) halosilane.

The unsaturated monomers illustrated by the general formula (IV) can be obtained as commercially available products (manufactured by Chisso Corporation) such as FP2231 (trade name;  $p = 30$ ,  $q = 5$ ,  $\text{R}_5$  = a methyl group and  $\text{R}_6$  = a phenyl group; referred to as polysiloxane FP2231 in the preparation example below), FP2241 and FP2242.

The polysiloxane group-containing unsaturated monomers illustrated by the general formulae (II) - (IV) can be copolymerized in the form as such. Alternatively, they can be copolymerized in the form of their precursor and a polysiloxane group will then be added. Specifically, a polysiloxane group can be introduced by copolymerizing the monomer in the form of (meth)acrylic acid and then reacting with a polysiloxane having a terminal epoxy group (for example, a compound illustrated by the following structural formula (1), this compound being referred to as polysiloxane FM0521 in the preparation example below). A polysiloxane group can also be introduced by polymerizing the monomer in the form of (meth)acryloyloxyalkylenedialkylchlorosilane and then reacting with a polysiloxane having a terminal epoxy group or a polysiloxane having a terminal modified with an amino group.

Structural formula (1):



The quantity of copolymerization of the polysiloxane group containing unsaturated monomer (b) is in the range of 0.1 to 85% by weight, preferably 0.5 to 70% by weight, more preferably 0.5 to 20% by weight, of the total monomer weight. If the amount is less than 0.1% by weight, the copolymer obtained cannot afford hair an excellent gloss and brilliance or a smooth feeling. If the amount of the monomer exceeds 85% by weight, it will cause problems when it is incorporated into cosmetics or when it is used repeatedly over a long period.

If the monomer represented by the formula (I) described above is monofunctional and the sum of m and n is 80 or more, the copolymerizability of the monomer decreases, so that it is effective to use a bifunctional monomer wherein R<sub>2</sub> is a vinyl group, an acryloyloxy group or a methacryloyloxy group in combination with the monofunctional monomer.

## Hydrophobic unsaturated monomer (c):

The hydrophobic unsaturated monomer of the component (c) is a hydrophobic unsaturated monomer having radical polymerizability which is used, if necessary, in order to afford the copolymer obtained a hydrophobic property and the strength, hardness and softness of film derived therefrom. The hydrophobic unsaturated monomer has preferably a solubility in water in the range of less than 10 g/100 g in water (25°C).

Examples of the hydrophobic unsaturated monomers include, for example, (a) saturated and unsaturated alkyl (meth)acrylates having 1 to 24 carbon atoms in the alkyl such as methyl (meth)acrylate, allyl (meth)acrylate, isobutyl (meth)acrylate, cyclohexyl (meth)acrylate, octyl (meth)acrylate, lauryl (meth)acrylate, oleyl (meth)acrylate, behenyl (meth)acrylate; (b) hydrophobic (meth)acrylates and their derivatives such as butoxyethyl (meth)acrylate, benzyl (meth)acrylate, tetrahydrofurfuryl (meth)acrylate, ethyleneglycol di(meth)acrylate, 1,3-butyleneglycol di(meth)acrylate, diacetoneacrylamide; (c) aromatic unsaturated monomers such as styrene, chlorostyrene, vinyltoluene; and (d) vinyl esters such as vinyl acetate.

The amount of the hydrophobic unsaturated monomer polymerized is in the range of 0 to 84.9% by weight to the total monomer weight, and this monomer is not an essential component. If the amount of this monomer exceeds 84.9% by weight, the copolymer thus obtained may have problems that it becomes hardly soluble in water and/or an ethanolic solvent or it is difficult to be removed from hair upon hair washing. The amount of the monomer can be selected at will according to the uses with the upper limit of 84.9% by weight. The hydrophobic unsaturated monomer is preferably used in an amount of 40 to 84.5% by weight when the polymer is used as a hair-setting polymer and 0 to 69.5% by weight when the polymer is used as a hair-conditioning polymer.

When a bifunctional unsaturated monomer such as ethyleneglycol di(meth)acrylate, allyl (meth)acrylate is used, it is preferably used in an amount of 2% by weight or less to the total monomer weight.

### Formation of copolymer

The unsaturated monomers can be copolymerized by well-known radical polymerization methods such as bulk polymerization, solution polymerization, suspension polymerization, emulsion polymerization.

Preferred polymerization method is a solution polymerization method, which is conducted by a process comprising dissolving monomers in a solvent, adding a polymerization initiator and stirring under heating the mixture under the nitrogen stream.

the solvent is preferably water and an alcohol such as methanol, ethanol, isopropanol, ethyleneglycol and butylcellosolve. These solvents can be used in combination. The polymerization initiator is preferably a peroxide such as benzoyl peroxide, lauroyl peroxide and an azo compound such as azobisisobutyronitrile or the like.

The monomers concerned are usually used in such a way that all of them in types and amounts are added to the polymerization at once from the initiation of polymerization, but alternatively they can be used in such a way that some of them in types and/or amounts are added to polymerization separately. The solvent is preferably used in such an amount that the copolymer solution obtained has a polymer concentration of 10 to 65% by weight. The amount of the monomers charged may be determined in consideration of factors such as the copolymerizability or the conversion so that the copolymer obtained has a predetermined composition. It goes without saying that the monomers charged has the same composition as that of the copolymer in the case of the conversion of 100%.

The molecular weight of the copolymer can be decided at will by appropriately selecting the polymerization conditions such as polymerization temperature, the kinds and amounts of polymerization initiators, addition methods, the amounts of solvent used, the chain transfer agents when used. In general, the copolymers obtained have preferably the molecular weight in the range of 1,000 to 500,000.

The copolymer can be obtained as a solid by removing the solvent from a copolymer solution, or the solid thus obtained can be diluted with any solvents to obtain a copolymer solution, which are used for further applications. The copolymers thus obtained and the solutions may be used in admixture of the two or more.

## [[II]] Use of the polymer/hair-care products

The copolymer thus obtained is preferably used as a polymer suitable for hair-care products in an amount of 0.1 to 10% by weight in well-known compositions such as shampoos, rinses, hair treatment products, hair setting products, cold permanent wave lotions. The hair-care products into which the copolymer is incorporated may be of any forms such as liquid, cream, emulsion, gel. It may also be used in combination with well-known conventional naturally occurring polymers, modified products of naturally occurring polymers or synthetic polymers.

Hair-care products in which the copolymer in accordance with the present invention is used include hair setting compositions for setting hair in desired hair style such as aerosol hair sprays, pump hair sprays, foaming type hair sprays, hair mists, hair setting lotions, hair styling gels, hair liquids, hair creams, hair oils, and those for providing hair with softness, gloss, smooth combing, recovery from damage, manageability such as shampoos, rinses, hair treatment lotions, cold permanent wave lotions.

More particularly, typical examples of hair-care products in which the copolymers in accordance with the present invention are incorporated are as follows.

### (1) Hair-care products for hair setting:

Hair-care products for hair setting include those in which water and/or an alcohol e.g. ethanol or isopropanol is used as a solvent known in the art such as aerosol hair spray, pump hair spray, foaming type hair spray, hair mist, hair-setting lotion, hair-styling gel, hair liquid, hair cream, hair oil.

The copolymers in accordance with the present invention are used in these hair-care products as a partial or total substitute for or in combination with anionic, nonionic, cationic and amphoteric polymers and polysiloxane polymers conventionally used in these hair-care products.

The copolymers in accordance with the present invention can also be used in hair-care products in combination with oils or fats, humectants, solubilizing agents, emulsifiers, thickeners, germicides, perfumes conventionally used in hair-care products.

For these uses, it is preferable that the copolymer comprises a unit of the hydrophilic monomer (a) in 15 to 59.5% by weight, a unit of the monomer comprising a polysiloxane group (b) in 0.5 to 45% by weight, and a unit of the hydrophobic monomer (c) in 40 to 84.5% by weight.

When the ionic natures of the hydrophilic monomer (a) are nonionic, anionic, amphoteric in that the monomer has cationic and anionic natures in its molecule, or amphoteric in that a cationic monomer and an anionic monomer are in admixture, it is preferable that a unit of the copolymer comprises the hydrophilic monomer (a) in 20 to 59.5% by weight, a unit of the monomer comprising a polysiloxane group (b) in 0.5 to 40% by weight, and a unit of the hydrophobic monomer (c) in 40 to 79.5% by weight.

When the hydrophilic monomer (a) is cationic, it is preferable that the copolymer comprises a unit of the hydrophilic monomer (a) in 15 to 54.5% by weight, a unit of the monomer comprising a polysiloxane group (b) in 0.5 to 45% by weight, and a unit of the hydrophobic monomer (c) in 40 to 84.5% by weight.

When the hydrophilic monomer (a) is amphoteric in that a cationic monomer and an anionic monomer are in admixture, the ratio by weight of cationic monomer units/anionic monomer units is preferably 1/9 to 9/1.

### (2) Hair-care products for hair conditioning

Hair-care products for hair conditioning include those in which water and/or an alcohol, e.g. ethanol or isopropanol is used as a solvent such as shampoos, hair rinses, cold permanent wave lotions and those in which water and/or an alcohol e.g. ethanol or isopropanol, or an alcohol and/or a hydrocarbon of a boiling point of 50 to 300°C such as hair treatment products.

When the hair-care products are shampoos in which the copolymers in accordance with the present invention are used, it is a conventional practice to use in the shampoos anionic, amphoteric or nonionic surfactants, and it is also possible to use in the shampoos foam improvers, thickeners, hydrotropes, emulsifiers, conditioning aids, germicides, perfumes.



When the hair-care products are hair-rinses in which the copolymers in accordance with the present invention are used, it is a conventional practice to use in the rinses cationic surfactants, and it is also possible to use in the rinses oils and fats, cationic surfactants, amphoteric surfactants, humectants, solubilizing agents, emulsifiers, thickeners, germicides, hair tonics, perfumes.

When the hair-care products are cold permanent wave lotions, it is a conventional practice to use in the lotions bromates, perborates, oxidation-reduction compositions e.g. thioglycolates or cysteine and the like. It is also possible to use in the lotion surfactants, thickeners, stabilizing agents, emulsifiers, conditioning aids, humectants, germicides, perfumes.

When the hair-care products are hair treatment products, the copolymers in accordance with the present invention are used in these hair treatment products as a partial or total substitute for or in combination with cationic surfactants and/or cationic polymers e.g. cationic polypeptides, cationic celluloses, cationic polysiloxanes. It is also possible to use in the hair treatment products oils and fats, amphoteric polymers, humectants, solubilizing agents, emulsifiers, thickeners, germicides, hair tonics, perfumes.

The copolymers in accordance with the invention when they are used in the hair treatment products are preferably such that the hydrophilic monomer (a) is cationic, amphoteric in that it has cationic and anionic natures in its molecule, or amphoteric in that a cationic monomer and an anionic monomer are in admixture. The hydrophilic monomers (a) may be used singly or in combination, but the ratio by weight of the units of a cationic hydrophilic monomer/the units of an anionic or amphoteric hydrophilic monomer which has anionic and cationic natures in its molecule is 1/9 to 9/1.

The copolymers in accordance with the present invention preferably comprises a unit of the hydrophilic monomer (a) in 30 to 99.5% by weight, a unit of the monomer comprising a polysiloxane group (b) in 0.5 to 70% by weight, and a unit of the hydrophobic monomer in 0 to 69.5% by weight. Specific embodiments are disclosed in the appended claims.

### [III] Examples

The present invention is explained more specifically with reference to the following preparation examples and formulation examples without limit thereto. The parts and percentages in the preparation examples are represented by weight. The parts and percentages in the formulation examples are represented by weight on the basis of effective components.

#### Preparation Example 1

In a five-neck flask equipped with a reflux condenser, a dropping funnel, a thermometer, a glass tube for nitrogen substitution and a stirrer are charged 70 parts of dimethylaminoethyl methacrylate, 25 parts of N-vinylpyrrolidone, 5 parts of polysiloxane FM0721 and 150 parts of anhydrous ethanol. A 0.6 part amount of azobisisobutyronitrile is added to the mixture, and the polymerization is carried out for 8 hours by heating under reflux at 80°C under a nitrogen stream.

Next, a 50% solution in anhydrous alcohol of propanesultone which is equimolar to the dimethylaminoethyl methacrylate is added dropwise from a dropping funnel into the five-neck flask and heated under reflux at 80°C for further 6 hours under a nitrogen stream in order to conduct amphoterization reaction. The polymer thus obtained is referred to as "P-1". In an actual practice, the polymer thus obtained had an average molecular weight of 170,000.

#### Preparation Example 2

In a five-neck flask similar to that in Preparation Example 1 are charged 30 parts of dimethylaminoethyl methacrylate, 70 parts of polysiloxane FM0711 and 200 parts of anhydrous ethanol. One part of azobisisobutyronitrile is added to the mixture, and the polymerization is carried out for 6 hours by heating under reflux at 80°C under a nitrogen stream.

Next, a 50% solution in anhydrous ethanol of propanesultone which is equimolar to the dimethylaminoethyl methacrylate is added dropwise from a dropping funnel into the five-neck flask and heated under reflux at 80°C under a nitrogen stream in order to conduct cationization reaction for further 6 hours. The polymer thus obtained is referred to as "P-2". In an actual practice, the polymer obtained had an average molecular weight of 25,000.

#### Preparation Example 3

In a five-neck flask similar to that in Preparation Example 1 are charged 85 parts of dimethylaminoethyl methacrylate, 11 parts of lauryl methacrylate, 3 parts of polysiloxane FM0725, 1 part of polysiloxane FP-2231 and 67 parts of anhydrous ethanol, and the mixture is heated under reflux at 80°C under a nitrogen stream. A solution of 0.6 part of azobisisobutyronitrile in 33 parts of ethanol is added to a five-neck flask by dropping from a dropping funnel over a period of 3 hours. Next, 0.3 part of azobisisobutyronitrile was added to the mixture, and the polymerization is carried out for further 6 hours by heating under reflux at 80°C under a nitrogen stream.

## EP 0 408 311 B1

Next, a 40% solution in anhydrous ethanol of an aminomethylpropanol neutralization product of monochloroacetic acid which is equimolar to the dimethylaminoethyl methacrylate is added dropwise from a dropping funnel into the five-neck flask and heated under reflux at 80°C for further 6 hours under a nitrogen stream in order to conduct amphoterization reaction.

Then, ethanol is removed by heating while pure water is added by from a dropping funnel to the five-neck flask so as to give an aqueous solution of the polymer. The polymer thus obtained is referred to as "P-3". In an actual practice the polymer obtained had an average molecular weight of 300,000.

### Preparation Example 4

In a five-neck flask similar to that in Preparation Example 1 are charged 40 parts of dimethylaminoethyl methacrylate, 35 parts of t-butyl methacrylate, 24 parts of tridecyl methacrylate, 1 part of polysiloxane FM0721 and 150 parts of anhydrous ethanol. 0.6 part of azobisisobutyronitrile is added, and the polymerization is carried out for 8 hours by heating under reflux at 80°C under a nitrogen stream.

Next, a 40% solution in anhydrous ethanol of a potassium hydroxide neutralization product of monochloroacetic acid which is equimolar to the dimethylaminoethyl methacrylate is added dropwise from a dropping funnel into the five-neck flask and heated under reflux at 80°C for further 12 hours under a nitrogen stream in order to conduct amphoterization reaction.

Suspended materials (potassium chloride) are removed by pressurized filtration from the viscous suspension thus obtained.

The filtrate is passed through a column in which a cation exchange resin ("DIAION PK-220", of which system has been substituted by anhydrous ethanol after regeneration) has been packed and is passed through a column in which an anion exchange resin ("DIAION PA-416", of which system has been substituted by anhydrous ethanol after regeneration) has been packed. The polymer thus obtained is referred to as "P-4". In an actual practice, the polymer obtained had an average molecular weight of 60,000.

### Preparation Example 5

In a five-neck flask similar to that in Preparation Example 1 are charged 70 parts of N-vinylpyrrolidone, 30 parts of polysiloxane FM0721 and 100 parts of anhydrous ethanol, and 0.6 part of azobisisobutyronitrile is added to the mixture. The polymerization is carried out for 8 hours by heating under reflux at 80°C under a nitrogen stream.

The polymer thus obtained is referred to as "P-5". In an actual practice, the polymer obtained had an average molecular weight of 150,000.

### Preparation Example 6

In a five-neck flask similar to that in Preparation Example 1 are charged 15 parts of acrylic acid, 5 parts of methacrylic acid, 10 parts of methyl acrylate, 40 parts of butyl methacrylate, 25 parts of lauryl methacrylate, 5 parts of polysiloxane FM0721 and 150 parts of anhydrous ethanol. 0.6 part of benzoyl peroxide is added, and the polymerization is carried out for 6 hours by heating under reflux at 80°C under a nitrogen stream.

Next, a 50% solution in anhydrous ethanol of triethanolamine which corresponds to 85% molar amount of the acid is added dropwise under cooling from a dropping funnel into the five-neck flask. The polymer thus obtained is referred to as "P-4". In an actual practice, the polymer obtained had an average molecular weight of 120,000.

### Preparation Example 7

In a five-neck flask similar to that in Preparation Example 1 are charged 45 parts of methacrylic acid, 10 parts of methyl methacrylate, 30 parts of iso-butyl methacrylate, 15 parts of palmityl methacrylate and 150 parts of toluene. 0.6 part of benzoyl peroxide is added, and the polymerization is carried out for 6 hours by heating under reflux at 80°C under a nitrogen stream.

Next, 1 part of benzyltrimethylammonium chloride is added, and 5 parts of polysiloxane FM-0521 is added dropwise from a dropping funnel into the five-neck flask in order to conduct addition reaction by heating under reflux at 80°C for 6 hours under a nitrogen stream.

Toluene in the toluene solution obtained is removed by evaporation by heating to give a precursor polymer as a solid. The polymer is dissolved in a 5% water-containing ethanol so that it has a concentration of 40%.

Next, a 50% solution in ethanol (containing 5% of water) of aminomethylpropanol which corresponds to 85% molar amount of the residual acid is added dropwise under cooling from a dropping funnel into the five-neck flask. The polymer thus obtained is referred to as "P-7". In an actual practice, the polymer obtained had an average molecular weight of

90,000.

Formulation Example 1

A shampoo composition having the following formulation was prepared.

Sodium polyoxyethylenelauryl sulfate (3EO)	16%
Lauroyl diethanolamide	2%
"P-1"	1.5%
Perfume	0.2%
Preservative	0.1%
Coloring matter	trace
Pure water	balance
	<u>100%</u>

When the composition was used for shampoos, hair after washing was combed smoothly, and the hair after drying had an excellent gloss and brilliance and a smooth feeling so that the hair was combed smoothly.

With repeated shampoos, adverse effects such as tackiness were not observed.

Formulation Example 2

A shampoo composition having the following formulation was prepared.

Sodium polyoxyethylenelauryl sulfate (3EO)	10%
Sodium lauryl sulfate	8%
Lauroyl diethanolamide	2%
"P-3"	1.5%
Pure water	<u>balance</u>
	<u>100%</u>

When the composition was used for shampoos, excellent effects as in Formulation Example 1 were obtained.

Formulation Example 3

A shampoo composition having the following formulation was prepared.

Coconut oil fatty acid dimethylaminosulfobetaine	10%
Sodium polyoxyethylenelauryl sulfate (3EO)	5%
"P-5"	0.5%
Pure water	balance
	<u>100%</u>

When the composition was used for shampoos, excellent effects as in Example 1 was obtained.

Formulation Example 4

A rinse composition having the following formulation was prepared.

Stearyltrimethylammonium chloride	1.5%
Cetanol	2%
"P-2"	0.2%

EP 0 408 311 B1

(continued)

Perfume	0.2%
Pure water	balance
	100%

When the composition was used for a rinse, hair after rinsing was combed smoothly, and the hair after drying had an excellent gloss and brilliance and a smooth feeling so that the hair was combed smoothly.

With repeated rinsings, adverse effects such as tackiness were not observed.

Formulation Example 5

A hair oil composition having the following formulation was prepared.

Octamethylcyclotetrasiloxane 40%

"P-2" 8%  
Anhydrous ethanol balance  
100%

When the composition was used for a rinse, hair after rinsing was combed smoothly, and the hair after drying had an excellent gloss and brilliance and a smooth feeling so that the hair was combed smoothly. When the hair oil composition was applied to hair and the hair was washed in repeated cycle, adverse effects such as tackiness or development of a feeling of physical disorder due to its accumulation were not observed.

Formulation Example 6

A diluted polymer solution of the following formulation was charged in a spraying can, which were then charged with a liquefied petroleum gas to prepare a hair spray composition.

A diluted polymer solution	
"P-2"	4 parts
Anhydrous ethanol	balance
	<u>65 parts</u>

Liquefied petroleum gas	
(3 kg/cm <sup>2</sup> G, 20°C)	35 parts

When the composition was used by spraying it onto hair, it afforded the hair an excellent set maintaining capability as well as an excellent gloss and brilliance and a smooth feeling. When the hair oil composition was applied to hair and the hair was washed in repeated cycle, adverse effects such as tackiness or a feeling of physical disorder due to its accumulation were not observed.

Formulation Example 7

In the same manner as in Formulation Example 6, a hair spray composition was prepared.

A diluted polymer solution	
"P-6"	3 parts
Anhydrous ethanol	balance
	<u>70 parts</u>

Liquefied petroleum gas	
(3 kg/cm <sup>2</sup> G, 20°C)	30 parts

When the composition was used by spraying it onto hair, an excellent effect like the Example 6 was obtained.

#### Formulation Example 8

In the same manner as in Formulation Example 6, a foaming aerosol composition was prepared.

A diluted polymer solution	
"P-4"	2 parts
YUKAFOMER AM-75R 205S*	2 parts
Polyoxyethylene cetyl ether (10EO)	0.3 parts
Polyoxyethylene cetyl ether (2EO)	0.1 parts
Pure water	balance
	88 parts

\*YUKAFOMER AM-75R 205S\* is a carboxybetaine type amphoteric polymer which is commercially available from MITSUBISHI PETROCHEMICAL CO., LTD.

Liquefied petroleum gas	
(3 kg/cm <sup>2</sup> G, 20°C)	12 parts

When the composition was used by applying it to hair, an excellent effect like the Formulation Example 6 was obtained.

#### Formulation Example 9


A hair set lotion composition having the following formulation was prepared.

"P-4"	3%
Pure water	60%
Anhydrous ethanol	balance
	100%

When the composition was used by spraying it onto hair, an excellent effect like the Formulation Example 6 was obtained.

#### Claims

- Use in a hair-care product of a copolymer comprising (a) a unit of a hydrophilic ethylenically unsaturated monomer in a quantity of 15 to 99.9% by weight; (b) a unit of an ethylenically unsaturated monomer having a polysiloxane group in a quantity of 0.1 to 85% by weight; and (c) a unit of a hydrophobic ethylenically unsaturated monomer in a quantity of 0 to 84.9% by weight.
- Use in a hair-care product according to claim 1, wherein the ethylenically unsaturated monomer having a polysiloxane group (b) comprises one or more of the monomers represented by the formula (I):



wherein D, R<sub>1</sub>, R<sub>2</sub>, m and n have the following meanings, respectively:

D = an unsaturated group having radical polymerizability selected from the group consisting of a vinyl group, a vinylalkylene group, a vinylhydroxyalkylene group, an acryloyloxyalkylene group, a methacryloyloxyalkylene group, an acryloyloxyhydroxyalkylene group and a methacryloyloxyhydroxyalkylene group;




R<sub>1</sub> = a hydrogen atom, a phenyl group, an alkyl group having 1 to 10 carbon atoms, a polyalkylene group, a polyoxyalkylene group of which end has been substituted by an ether or ester group, a polyalkylenepolyamine group, a fatty acid group or a polysiloxane group, respectively;

R<sub>2</sub> = a hydrogen atom, a phenyl group, an alkyl group having 1 to 10 carbon atoms, a polyalkylene group, a polyoxyalkylene group of which end has been substituted by an ether or ester group, a polyalkylenepolyamine group, a fatty acid group or a polysiloxane group, or an unsaturated group having radical polymerizability selected from the group consisting of a vinyl group, a vinylalkylene group, a vinylhydroxyalkylene group, an acryloyloxyalkylene group or a methacryloyloxyalkylene group;

m = an integer from 4 to 150; and

n = an integer from 0 to 150, wherein the sum of m and n is within 150.

3. Use in a hair-care product according to claim 1, wherein the ethylenically unsaturated monomer having a polysiloxane group (b) comprises one or a mixture of the two or more of the monomers represented by the formulae (II) to (IV):



wherein R<sub>3</sub> to R<sub>5</sub>, p and q have the following meanings independently of each other between the formulae:

R<sub>3</sub> = a hydrogen atom or a methyl group;

R<sub>4</sub> = an alkylene group having 1 to 4 carbon atoms;

R<sub>5</sub> = an alkyl group having 1 to 10 carbon atoms or a phenyl group;

p = an integer of 1 or more; and

q = an integer of 1 or more, wherein the sum of p and q are within 150.


4. Use in a hair-care product according to claim 1, wherein the hydrophilic unsaturated monomer (a) comprises a nonionic unsaturated monomer.
- 5 5. Use in a hair-care product according to claim 1, wherein the hydrophilic monomer (a) comprises an anionic unsaturated monomer.
6. Use in a hair-care product according to claim 1, wherein the hydrophilic monomer (a) comprises a cationic unsaturated monomer.
- 10 7. Use in a hair-care product according to claim 1, wherein the hydrophilic unsaturated monomer (a) comprises an amphoteric unsaturated monomer in that the monomer has an anionic nature and a cationic nature in its molecule.
8. Use in a hair-care product according to claim 1, wherein the hydrophilic unsaturated monomer (a) comprises a mixture of at least two of monomers consisting of a nonionic unsaturated monomer, an anionic unsaturated monomer, a cationic unsaturated monomer, and an amphoteric unsaturated monomer in that the monomer has an anionic nature and a cationic nature in its molecule.
- 15 9. Use in a hair-care product according to claim 1, wherein the copolymer comprises (a) a unit of a hydrophilic unsaturated monomer selected from the group consisting of a nonionic monomer, an anionic monomer, an amphoteric monomer in that the monomer has an anionic nature and a cationic nature in its molecule, and a mixture thereof, in a quantity of 20 to 59.5% by weight; (b) a unit of an unsaturated monomer having a polysiloxane group, in a quantity of 0.5 to 40% by weight; and (c) a unit of a hydrophobic unsaturated monomer, in a quantity of 40 to 79.5% by weight, the polymer being suitable for use in hair-setting.
- 20 10. Use in a hair-care product according to claim 1, wherein the copolymer comprises (a) a unit of a hydrophilic monomer which is a mixture of a cationic unsaturated monomer and an anionic unsaturated monomer, the weight ratio of the cationic monomer to the anionic monomer being 1/9 to 9/1, in a quantity of 20 to 59.5% by weight, (b) a unit of the unsaturated monomer having a polysiloxane group, in a quantity of 0.5 to 40% by weight; and (c) a unit of a hydrophobic unsaturated monomer, in a quantity of 40 to 79.5% by weight, the polymer being suitable for hair setting.
- 25 30 11. Use in a hair-care product according to claim 1, wherein the copolymer comprises (a) a unit of a hydrophilic unsaturated monomer which is cationic, in a quantity of 15 to 54.5% by weight; (b) a unit of an unsaturated monomer having a polysiloxane group, in a quantity of 0.5 to 45% by weight; and (c) a unit of a hydrophobic unsaturated monomer, in a quantity of 40 to 84.5% by weight, the polymer being suitable for hair setting.
- 35 12. Use in a hair-care product according to claim 1, wherein the copolymer comprises (a) a unit of a hydrophilic unsaturated monomer, in a quantity of 15 to 99.5% by weight, (b) a unit of an unsaturated monomer having a polysiloxane group, in a quantity of 0.5 to 20% by weight and (c) a unit of a hydrophobic unsaturated monomer, in a quantity of 0 to 84.5% by weight.
- 40 13. Use in a hair-care product according to claim 1, wherein the copolymer comprises (a) a unit of a hydrophilic unsaturated monomer which is a cationic monomer or an amphoteric monomer in that the monomer has an anionic nature and a cationic nature in its molecule, in a quantity of 30 to 99.5% by weight; (b) a unit of an unsaturated monomer having a polysiloxane group, in a quantity of 0.5 to 70% by weight; and (c) a unit of a hydrophobic unsaturated monomer, in a quantity of 0 to 69.5% by weight, the polymer being suitable for hair conditioning.
- 45 14. Use in a hair-care product according to claim 1, wherein the copolymer comprises (a) a unit of a hydrophilic monomer which is a combination of a cationic monomer and an anionic monomer or which is a combination of a cationic monomer and an amphoteric monomer in that the monomer has an anionic nature and a cationic nature in its molecule, the weight ratio of the cationic monomer to the anionic monomer or to the amphoteric monomer being 1/9 to 9/1, in a quantity of 30 to 99.5% by weight; (b) a unit of an unsaturated monomer having a polysiloxane group, in a quantity of 0.5 to 70% by weight; and (c) a unit of hydrophobic unsaturated monomer, in a quantity of 0 to 69.5% by weight, the polymer being suitable for hair conditioning.
- 50 55 15. A hair-care product comprising a copolymer comprising (a) a unit of a hydrophilic ethylenically unsaturated monomer in a quantity of 15 to 99.9% by weight; (b) a unit of an ethylenically unsaturated monomer having a polysiloxane group in a quantity of 0.1 to 85% by weight; and (c) a unit of an hydrophobic ethylenically unsaturated

monomer in a quantity of 0 to 84.9% by weight, which copolymer is dissolved in water and/or an alcohol in a concentration of 0.5 to 10% by weight.

16. A hair-care product according to claim 15, comprising the copolymer dissolved in a concentration of 0.5 to 10% by weight in a hydrocarbon of a boiling temperature of 50 to 300°C or in a mixture of the hydrocarbon with an alcohol.

### Patentansprüche

1. Verwendung eines Copolymeren, das (a) eine Einheit aus einem hydrophilen ethylenartig ungesättigten Monomeren in einer Menge von 15 bis 99,9 Gew.%; (b) eine Einheit aus einem ethylenartig ungesättigten Monomeren, das eine Polysiloxangruppe hat, in einer Menge von 0,1 bis 85 Gew.%; und (c) eine Einheit aus einem hydrophoben ethylenartig ungesättigten Monomeren in einer Menge von 0 bis 84,9 Gew.% enthält, in einem Haarpflegeprodukt.
2. Verwendung in einem Haarpflegeprodukt nach Anspruch 1, wobei das ethylenartig ungesättigte Monomer, das eine Polysiloxangruppe hat, (b) ein oder mehrere Monomere, die durch die Formel (I) dargestellt werden, enthält:



worin D, R<sub>1</sub>, R<sub>2</sub>, m und n jeweils die folgenden Bedeutungen haben:

D = eine ungesättigte Gruppe mit radikalischer Polymerisierbarkeit, die aus der aus einer Vinylgruppe, einer Vinylalkylengruppe, einer Vinylhydroxyalkylengruppe, einer Acryloyloxyalkylengruppe, einer Methacryloyloxyalkylengruppe, einer Acryloyloxyhydroxyalkylengruppe und einer Methacryloyloxyhydroxyalkylengruppe bestehenden Gruppe ausgewählt ist;


R<sub>1</sub> = jeweils ein Wasserstoffatom, eine Phenylgruppe, eine Alkylgruppe mit 1 bis 10 Kohlenstoffatomen, eine Polyalkylengruppe, eine Polyoxyalkylengruppe, deren Ende mit einer Ether- oder Estergruppe substituiert worden ist, eine Polyalkylenpolyaminygruppe, eine Fettsäuregruppe oder eine Polysiloxangruppe;

R<sub>2</sub> = ein Wasserstoffatom, eine Phenylgruppe, eine Alkylgruppe mit 1 bis 10 Kohlenstoffatomen, eine Polyalkylengruppe, eine Polyoxyalkylengruppe, deren Ende mit einer Ether- oder Estergruppe substituiert worden ist, eine Polyalkylenpolyaminygruppe, eine Fettsäuregruppe oder eine Polysiloxangruppe oder eine ungesättigte Gruppe mit radikalischer Polymerisierbarkeit, die aus der aus einer Vinylgruppe, einer Vinylalkylengruppe, einer Vinylhydroxyalkylengruppe, einer Acryloyloxyalkylengruppe oder einer Methacryloyloxyalkylengruppe bestehenden Gruppe ausgewählt ist;



m = eine ganze Zahl zwischen 4 und 150; und

n = eine ganze Zahl zwischen 0 und 150, wobei die Summe aus m und n im Zahlenbereich bis 150 liegt.

3. Verwendung in einem Haarpflegeprodukt nach Anspruch 1, wobei das ethylenartig ungesättigte Monomer, das eine Polysiloxangruppe hat, (b), eine Monomer oder ein Gemisch aus zwei oder mehreren Monomeren, das (die) durch die Formeln (II) bis (IV) dargestellt wird (werden), enthält:







worin  $\text{R}_3$  bis  $\text{R}_5$ ,  $p$  und  $q$  unabhängig voneinander in den einzelnen Formeln die folgenden Bedeutungen haben:

- $\text{R}_3$  = ein Wasserstoffatom oder eine Methylgruppe;  
 $\text{R}_4$  = eine Alkylengruppe mit 1 bis 4 Kohlenstoffatomen;  
 $\text{R}_5$  = eine Alkylgruppe mit 1 bis 10 Kohlenstoffatomen oder eine Phenylgruppe;  
 $p$  = eine ganze Zahl 1 oder mehr; und  
 $q$  = eine ganze Zahl 1 oder mehr, wobei die Summe aus  $p$  und  $q$  im Zahlenbereich bis 150 liegt.


4. Verwendung in einem Haarpflegeprodukt nach Anspruch 1, wobei das hydrophile ungesättigte Monomer (a) ein nichtionisches ungesättigtes Monomer umfaßt.
5. Verwendung in einem Haarpflegeprodukt nach Anspruch 1, wobei das hydrophile Monomer (a) ein anionisches ungesättigtes Monomer umfaßt.
6. Verwendung in einem Haarpflegeprodukt nach Anspruch 1, wobei das hydrophile Monomer (a) ein kationisches ungesättigtes Monomer umfaßt.
7. Verwendung in einem Haarpflegeprodukt nach Anspruch 1, wobei das hydrophile ungesättigte Monomer (a) ein amphoterer ungesättigtes Monomer umfaßt, in dem das Monomer in seinem Molekül eine anionische Natur und eine kationische Natur aufweist.
8. Verwendung in einem Haarpflegeprodukt nach Anspruch 1, wobei das hydrophile ungesättigte Monomer (a) ein Gemisch aus mindestens zwei Monomeren, die aus einem nicht-ionischen ungesättigten Monomeren, einem anionischen Monomeren, einem kationischen ungesättigten Monomeren und einem amphoteren ungesättigten Monomeren, wobei dieses Monomer in seinem Molekül eine anionische Natur und eine kationische Natur aufweist, bestehen, umfaßt.
9. Verwendung in einem Haarpflegeprodukt nach Anspruch 1, wobei das Copolymer (a) eine Einheit aus einem hydrophilen ungesättigten Monomeren, das aus der aus einem nicht-ionischen Monomeren, einem anionischen Monomer, einem amphoteren Monomer, das in seinem Molekül eine anionische Natur und eine kationische Natur aufweist, bestehenden Gruppe ausgewählt ist, in einer Menge von 20 bis 59,5 Gew.%; (b) eine Einheit aus einem ungesättigten Monomeren, das eine Polysiloxangruppe hat, in einer Menge von 0,5 bis 40 Gew.%; und (c) eine Einheit aus einem hydrophoben ungesättigten Monomeren in einer Menge von 40 bis 79,5 Gew.% enthält, und das Polymer zur Verwendung beim Haarfestigen geeignet ist.
10. Verwendung eines Haarpflegeprodukt nach Anspruch 1, wobei das Copolymer (a) eine Einheit aus einem hydrophilen ungesättigten Monomeren, das ein Gemisch aus einem kationischen ungesättigten Monomeren und einem anionischen ungesättigten Monomeren ist, und in dem das Gewichtsverhältnis des kationischen Monomeren zu dem anionischen Monomeren zwischen 1/9 und 9/1 liegt, in einer Menge von 20 bis 59,9 Gew.%; (b) eine Einheit aus dem ungesättigten Monomeren, das eine Polysiloxangruppe hat, in einer Menge von 0,5 bis 40 Gew.%; und (c) eine Einheit aus einem hydrophoben ungesättigten Monomeren in einer Menge von 40 bis 79,5 Gew.% enthält,

und das Polymer zum Haarfestigen geeignet ist.

11. Verwendung in einem Haarpflegeprodukt nach Anspruch 1, wobei das Copolymer (a) eine Einheit aus einem hydrophilen ungesättigten Monomeren, das kationisch ist, in einer Menge von 15 bis 54,5 Gew.%; (b) eine Einheit aus einem ungesättigten Monomeren, das eine Polysiloxangruppe hat, in einer Menge von 0,5 bis 45 Gew.%; und (c) eine Einheit aus einem hydrophoben ungesättigten Monomeren in einer Menge von 40 bis 84,5 Gew.% enthält, und das Polymer zum Haarfestigen geeignet ist.
12. Verwendung eines Haarpflegeproduktes nach Anspruch 1, wobei das Copolymer (a) eine Einheit aus einem hydrophilen ungesättigten Monomeren in einer Menge von 15 bis 99,5 Gew.%; (b) eine Einheit aus einem ungesättigten Monomeren, das eine Polysiloxangruppe hat, in einer Menge von 0,5 bis 20 Gew.%; und (c) eine Einheit aus einem hydrophoben ungesättigten Monomeren in einer Menge von 0 bis 84,5 Gew.% enthält.
13. Verwendung in einem Haarpflegeprodukt nach Anspruch 1, wobei das Copolymer (a) eine Einheit aus einem hydrophilen ungesättigten Monomeren, das ein kationisches Monomer oder ein amphoterisches Monomer, in dem das Monomer eine anionische Natur und eine kationische Natur in seinem Molekül aufweist, ist, in einer Menge von 30 bis 99,5 Gew.%; (b) eine Einheit aus einem ungesättigten Monomeren, das eine Polysiloxangruppe hat, in einer Menge von 0,5 bis 70 Gew.%; und (c) eine Einheit aus einem hydrophoben ungesättigten Monomeren in einer Menge von 0 bis 69,5 Gew.% enthält, und das Polymer zum Haarkonditionieren geeignet ist.
14. Verwendung in einem Haarpflegeprodukt nach Anspruch 1, wobei das Copolymer (a) eine Einheit aus einem hydrophilen Monomeren, das eine Kombination aus einem kationischen Monomeren und einem anionischen Monomeren ist oder das eine Kombination aus einem kationischen Monomeren und einem amphoterischen Monomeren, in dem dieses Monomer eine anionische Natur und eine kationische Natur in seinem Molekül aufweist, ist, worin das Gewichtsverhältnis des kationischen Monomeren zu dem anionischen Monomeren oder zu dem amphoterischen Monomeren zwischen 1/9 und 9/1 liegt, in einer Menge von 30 bis 95 Gew.%; (b) eine Einheit aus einem ungesättigten Monomeren, das eine Polysiloxangruppe hat, in einer Menge von 0,5 bis 70 Gew.%; und (c) eine Einheit aus einem hydrophoben ungesättigten Monomeren in einer Menge von 0 bis 69,5 Gew.% enthält, und das Polymer zur Haarkonditionierung geeignet ist.
15. Haarpflegeprodukt, das ein Copolymer enthält, welches (a) eine Einheit aus einem hydrophilen ethylenartig ungesättigten Monomeren in einer Menge von 15 bis 99,9 Gew.%; (b) eine Einheit aus einem ethylenartig ungesättigten Monomeren, das eine Polysiloxangruppe hat, in einer Menge von 0,1 bis 85 Gew.%; und (c) eine Einheit aus einem hydrophoben ethylenartig ungesättigten Monomeren in einer Menge von 0 bis 84,9 Gew.% umfaßt, und in dem das Copolymer in einer Konzentration von 0,5 bis 10 Gew.% in Wasser und/oder einem Alkohol aufgelöst ist.
16. Haarpflegeprodukt nach Anspruch 15, das das Copolymer, das in einer Konzentration von 0,5 bis 10 Gew.% in einem Kohlenwasserstoff mit einer Siedetemperatur zwischen 50 und 300°C oder in einem Gemisch des Kohlenwasserstoffs mit einem Alkohol aufgelöst ist, enthält.

#### Revendications

1. Utilisation, dans un produit pour les soins des cheveux, d'un copolymère comprenant (a) un motif d'un monomère hydrophile à insaturation éthylénique en une quantité de 15 à 99,9 % en poids ; (b) un motif d'un monomère à insaturation éthylénique ayant un groupe polysiloxane, en une quantité de 0,1 à 85 % en poids ; et (c) un motif d'un monomère hydrophobe à insaturation éthylénique en une quantité de 0 à 84,9 % en poids.
2. Utilisation, dans un produit pour les soins des cheveux selon la revendication 1, dans laquelle le monomère à insaturation éthylénique ayant un groupe polysiloxane (b) comprend un ou plusieurs des monomères représentés par la formule (I) :



dans laquelle D, R<sub>1</sub>, R<sub>2</sub>, m et n ont respectivement les significations suivantes :

D est un groupe insaturé pouvant être polymérisé par polymérisation radicalaire, choisi parmi l'ensemble comprenant le groupe vinyle, les groupes vinylalkylène, les groupes vinylhydroxyalkylène, les groupes acryloyloxyalkylène, les groupes méthacryloyloxyalkylène, les groupes acryloyloxyhydroxyalkylène et les groupes méthacryloyloxyhydroxyalkylène ;




R<sub>1</sub> est un atome d'hydrogène, un groupe phényle, un groupe alkyle ayant de 1 à 10 atomes de carbone, un groupe polyalkylène, un groupe polyoxyalkylène dont l'extrémité a été remplacée par un groupe éther ou ester, un groupe polyalkylène polyamine, un groupe acide gras ou un groupe polysiloxane, respectivement ;

R<sub>2</sub> est un atome d'hydrogène, un groupe phényle, un groupe alkyle ayant de 1 à 10 atomes de carbone, un groupe polyalkylène, un groupe polyoxyalkylène dont l'extrémité a été remplacée par un groupe éther ou ester, un groupe polyalkylène polyamine, un groupe acide gras ou un groupe polysiloxane, ou encore un groupe insaturé polymérisable par polymérisation radicalaire, choisi parmi l'ensemble comprenant le groupe vinyle, les groupes vinylalkylène, les groupes vinylhydroxyalkylène, les groupes acryloyloxyalkylène et les groupes méthacryloyloxyalkylène ;

m est un entier de 4 à 150 ; et

n est un entier de 0 à 150, la somme de m et de n étant inférieure ou égale à 150.

3. Utilisation, dans un produit pour les soins des cheveux selon la revendication 1, où le monomère à insaturation éthylénique ayant un groupe polysiloxane (b) comprend l'un des monomères ou un mélange d'au moins deux des monomères représentés par les formules (II) à (IV) :



dans lesquelles R<sub>3</sub> à R<sub>5</sub>, p et q ont les significations suivantes, indépendamment les uns des autres entre les différentes formules :

R<sub>3</sub> est un atome d'hydrogène ou un groupe méthyle ;

R<sub>4</sub> est un groupe alkylène ayant de 1 à 4 atomes de carbone ;

R<sub>5</sub> est un groupe alkyle ayant de 1 à 10 atomes de carbone ou un groupe phényle ;

p est un entier valant 1 ou plus ; et

q est un entier valant 1 ou plus, la somme de p et de q étant inférieure ou égale à 150.

4. Utilisation dans un produit pour les soins des cheveux selon la revendication 1, dans laquelle le monomère à insaturation hydrophile (a) comprend un monomère insaturé nonionique.

5. Utilisation dans un produit pour les soins des cheveux selon la revendication 1, dans laquelle le monomère hydrophile (a) comprend un monomère insaturé anionique.
6. Utilisation dans un produit pour les soins des cheveux selon la revendication 1, dans laquelle le monomère hydrophile (a) comprend un monomère insaturé cationique.
7. Utilisation dans un produit pour les soins des cheveux selon la revendication 1, dans laquelle le monomère insaturé hydrophile (a) comprend un monomère insaturé amphotère, en ce sens que le monomère a dans sa molécule une nature anionique et une nature cationique.
8. Utilisation dans un produit pour les soins des cheveux selon la revendication 1, dans laquelle le monomère insaturé hydrophile (a) comprend un mélange d'au moins deux monomères, constitué d'un monomère insaturé nonionique, d'un monomère insaturé anionique, d'un monomère insaturé cationique et d'un monomère insaturé amphotère, en ce sens que le monomère a une nature anionique et une nature cationique dans sa molécule.
9. Utilisation dans un produit pour les soins des cheveux selon la revendication 1, dans laquelle le copolymère comprend (a) un motif d'un monomère insaturé hydrophile choisi parmi l'ensemble comprenant les monomères nonioniques, les monomères anioniques, les monomères amphotère en ce sens que les monomères ont dans leur molécule une nature anionique et une nature cationique, et leurs mélanges, en une quantité de 20 à 59,5 % en poids ; (b) un motif d'un monomère insaturé ayant un groupe polysiloxane, en une quantité de 0,5 à 40 % en poids ; et (c) un motif d'un monomère insaturé hydrophobe, en une quantité de 40 à 79,5 % en poids, le polymère convenant à une utilisation dans une mise en pli.
10. Utilisation dans un produit pour les soins des cheveux selon la revendication 1, dans laquelle le copolymère comprend (a) un motif d'un monomère hydrophile qui est un mélange d'un monomère insaturé cationique et d'un monomère insaturé anionique, le rapport pondéral du monomère cationique au monomère anionique, étant de 1/9 à 9/1, en une quantité de 20 à 59,5 % en poids, (b) un motif du monomère insaturé ayant un groupe polysiloxane, en une quantité de 0,5 à 40 % en poids ; et (c) un motif d'un monomère insaturé hydrophobe, en une quantité de 40 à 79,5 % en poids, le polymère convenant à une mise en pli.
11. Utilisation dans un produit pour les soins des cheveux selon la revendication 1, dans laquelle le copolymère comprend (a) un motif d'un monomère insaturé hydrophile qui est cationique, en une quantité de 15 à 54,5 % en poids, (b) un motif d'un monomère insaturé ayant un groupe polysiloxane, en une quantité de 0,5 à 45 % en poids ; et (c) un motif d'un monomère insaturé hydrophobe, en une quantité de 40 à 84,5 % en poids, le polymère convenant à une mise en pli.
12. Utilisation dans un produit pour les soins des cheveux selon la revendication 1, dans laquelle le copolymère comprend (a) un motif d'un monomère insaturé hydrophile, en une quantité de 15 à 99,5 % en poids, (b) un motif d'un monomère insaturé ayant un groupe polysiloxane, en une quantité de 0,5 à 20 % en poids ; et (c) un motif d'un monomère insaturé hydrophobe, en une quantité de 0 à 84,5 % en poids.
13. Utilisation dans un produit pour les soins des cheveux selon la revendication 1, dans laquelle le copolymère comprend (a) un motif d'un monomère insaturé hydrophile qui est un monomère cationique ou un monomère amphotère en ce sens que le monomère a dans sa molécule une nature anionique et une nature cationique, en une quantité de 30 à 99,5 % en poids ; (b) un motif d'un monomère insaturé ayant un groupe polysiloxane, en une quantité de 0,5 à 70 % en poids ; et (c) un motif d'un monomère insaturé hydrophobe, en une quantité de 0 à 69,5 % en poids, le polymère convenant au conditionnement des cheveux.
14. Utilisation dans un produit pour les soins des cheveux selon la revendication 1, dans laquelle le copolymère comprend (a) un motif d'un monomère hydrophile qui est une combinaison d'un monomère cationique et d'un monomère anionique, ou qui est une combinaison d'un monomère cationique et d'un monomère amphotère, en ce sens que le monomère a dans sa molécule une nature anionique et une nature cationique, le rapport pondéral du monomère cationique au monomère anionique ou au monomère amphotère étant de 1/9 à 9/1, en une quantité de 30 à 99,5 % en poids, (b) un motif d'un monomère insaturé ayant un groupe polysiloxane, en une quantité de 0,5 à 70 % en poids ; et (c) un motif d'un monomère insaturé hydrophobe, en une quantité de 0 à 69,5 % en poids, le polymère convenant au conditionnement des cheveux.
15. Produit pour les soins des cheveux, comprenant un copolymère comprenant (a) un motif d'un monomère hydrophile

## EP 0 408 311 B1

à insaturation éthylénique, en une quantité de 15 à 99,9 % en poids ; (b) un motif d'un monomère à insaturation éthylénique ayant un groupe polysiloxane, en une quantité de 0,1 à 85 % en poids ; et (c) un motif d'un monomère hydrophobe à insaturation éthylénique en une quantité de 0 à 84,9 % en poids, le copolymère étant dissous dans de l'eau et/ou dans un alcool à une concentration de 0,5 à 10 % en poids.

- 5
16. Produit pour les soins des cheveux selon la revendication 15, comprenant le copolymère dissous à une concentration de 0,5 à 10 % en poids dans un hydrocarbure ayant une température d'ébullition de 50 à 300°C, ou dans un mélange de l'hydrocarbure avec un alcool.
- 10
- 15
- 20
- 25
- 30
- 35
- 40
- 45
- 50
- 55